GTC Paints Company Ltd.

P.O. Box: 24445 Safat - 13105 - Kuwait Sabhan Tel.: 24710120 - Fax: 24761261 Shuwaikh Tel.: 24848285 - Fax: 24837138 Capital: K.D. 1,000,000 - C.R.: 20117

FLASH POINT



شركة أصباغ جي تي سي المحدودة

ص.ب: 24445 الصفاة - 13105 - الكويت صبحان - تلفون : 24710120 - فاكس : 24761261 الشويخ - تلفون : 24848285 - فاكس : 24837138 رأس المال : 1,000,000 د.ك - س.ت : 20117

GETOXY (GEF Series/GEC055) FINISH

PRODUCT DESCRIPTION:

A two pack high performance Amine-aduct Cured Epoxy Finish Paint Coating suitable for application in New Construction/Maintenance and Repair Projects.

SPECIAL FEATURES	:					
	Tough and very good abrasion resistance.					
	Excellent adhesion over various types of substrates providing a hard cosmetic finish.					
	Offers a hard wearing film resistant to spillages and fumes of mild acids, alkalin					
	solutions and sea water.					
	Resistant to aromatic and hydro-carbon solvents, fuels and industrial detergents.					
	Resistant to Various mineral Oils.					
	iiiicia	i Olis.				
AREA OF USES:					v 20.0	
As an Internal/External intermed etc. i.e.	liate an	d/or finish coat on concrete, st	eel, wood, gy	ypsum board	, bricks, stone	
	ufo o o o	(steel company)				
☐ Various types of floor su☐ Internal and external wa						
☐ Concrete and steel chimn		masonry.				
		ns exposed to sea and aggressiv		stal annditin		
1	ruction	is exposed to sea and aggressiv	e environmei	itai conditioi	18.	
PRODUCT DATA:						
FINISH	:	GLOSS				
COLOUR	:	According to GTC GLOSS	ENAMEL COI	LOUR CARD F	RANGE	
		Including Black & White				
VOLUME SOLIDS		50%				
PRODUCT WEIGHT	:					
PRODUCT WEIGHT		1.45 kg/ltr.				
REC. FILM THICKNESS		Wet: 100 microns p				
	•	Dry : 50 microns pe	er coat (app	rox. 2 mils))	
THEO. COVERAGE	:	10 m ² /ltr.				
		Practical coverage primarily de	epends upon i	nature of surf	face profile,	
		method of application and site				
MIXING RATIO	:	Base : Curing Ag	ent			
			olume)			
		Ambient Temperature	10 °C	25 °C	40°C	
POT LIFE	:		50 °F	77 °F	104 °F	
		No. of Hours	10 hrs.	8 hrs.	4hrs.	
		Base : 23	°C (73 °F)			

Curing Agent : 23 °C (73 °F)

: 23 °C (73 °F)

Mixed

GTC Paints Company Ltd.

P.O. Box: 24445 Safat - 13105 - Kuwait Sabhan Tel.: 24710120 - Fax: 24761261 Shuwaikh Tel.: 24848285 - Fax: 24837138 Capital: K.D. 1,000,000 - C.R.: 20117



شركة أصباغ جي تي سي المحدودة

ص.ب: 24445 الصفاة - 13105 - الكويت صبحان - تلفون : 24710120 - فاكس : 24761261 الشويخ - تلفون : 24848285 - فاكس : 24837138 رأس المال : 1,000,000 د.ك - س.ت : 20117

DRYING TIME:

SUBSTRATE	TOUCH	HARD	FULL CURE	OVERCOATIN	IG INTERVALS
TEMPERATURE	DRY	DRY	TIME	MINIMUM	MAXIMUM
10 °C (50 °F)	5 hrs.	24 hrs.	10 days	20 hrs.	IND.
25 °C (77 °F)	3 hrs.	18 hrs.	1 week	16 hrs.	IND.
40 °C (104°F)	2 hrs.	14 hrs.	1 week	12 hrs.	IND.

STANDARDS & APPROVALS:

Supportive information is available upon request to establish an assessment to be acquired as with regards to product's compliance with/to a particular authority's queries specifications. Please consult with GTC Technical Service Dept.

SURFACE PREPARATION:

- 1. Degrease areas where grease, oil, soil and surface contamination exist in accordance with SSPC-SP1 Solvent Cleaning. (Use GTC002 Thinner).
- 2. Wire Brush/Mechanical Power Tool Cean areas where laitance, surface porosity and loosely adhering foreign material exist in accordance with SSPC-SP2 and/or SSPC-SP3 Standards.
- 3. Steel should be abrasive blast cleaned in accordance with SSPC-SP10 Standard (SA2½ Swedish Standard) and suitably primed as per individual situation depending upon type of substrate. Please consult with GTC Technical Service Dept.
- 4. Surfaces to be coated must be dry, clean and contamination free prior to paint and application process.

APPLICATION DETAILS:

☐ PURPOSE OF USAGE:

Intended for two or three coat applications over well prepared and suitably primed steel, concrete and a variety of other substrates / surfaces.

☐ MIXING & THINNING:

Material must be properly mixed and is recommended for thinning with **GTC099 Thinner** as per below table:-

Application Method	Brush/	Conv.	Airless
	Roller	Spray	Spray
Thinning by Vol (% Max.)	10 %	15%	5 %

GTC Paints Company Ltd.

P.O. Box: 24445 Safat - 13105 - Kuwait Sabhan Tel.: 24710120 - Fax: 24761261 Shuwaikh Tel.: 24848285 - Fax: 24837138 Capital: K.D. 1,000,000 - C.R.: 20117



شركة أصباغ جي تي سي المحدودة

ص.ب: 24445 الصفاة - 13105 - الكويت صبحان - تلفون : 24710120 - فاكس : 24761261 الشويخ - تلفون : 24848285 - فاكس : 24837138 رأس المال : 1,000,000 د.ك - س.ت : 20117

□ NOTES:

- 1) Curing Agent Code varies according to colours as follows:-
 - Black & Red Colours (GEC066)
 - All other colors (GEC055)
- 2) For maximum performance, curing temperatures should be above 10 °C (50 °F) since material will not adequately cure below 5 °C (41 °F).
- 3) Two pack epoxies are commonly known to chalk upon external exposure.
- 4) It is not recommended to apply two pack epoxy material over 50 °C (122 °F).

☐ CLEANING:

For cleaning tools and equipments use GTC099 Thinner.

APPLICATION CONDITIONS:-

At a temperature ranging 5°C (41°F) to 40°C (104 °F). Relative humidity is below 75%.

STORAGE & HANDLING:-

Product must be stored as per local regulations and should be kept in dry well ventilated location far from heat and direct sunlight. Can should be tightly closed after use. Mix well before use. Storage temperature range between 5°C (41°F) to 40°C (104 °F).

SAFETY PRECAUTIONS:

The following notes should be considered when using/applying painting material:-

- (a) Take precautions to prevent material entering the eyes (goggles should be worn, irrigate the eyes with water when become contaminated and obtain medical care at once).
- (b) Take precautions to avoid skin contact (gloves should be worn, barrier cream should be used).
- (c) Ensure that repeated contact of paint with skin is avoided.
- (d) Provide adequate ventilation. (Face masks must be worn).
- (e) Keep away from sparks and open flames (for solvent-based materials).

DISCLAIMER:

- The information given in this data sheet is for guidance only and is done to the best of our knowledge at the date of printing/issuing.
- GTC reserves the right to change the content of this data without any prior notice.
- Since we have no control over either the nature or condition of the substrate or different factors which effect the use and application of our products; therefore, no liability can be accepted on basis of this data sheet, unless we specifically agree in writing as to the suitability of the recommended product for the intended purpose; and furthermore, application of this product should be carried out under our control and direct supervision.
- Product data are subject to change without notice and become void five years from the date of issue.

PACKING	:	White:-
		☐ 3.6 Ltr Tins (Base + Curing Agent)
		☐ 18 Ltr Tins (Base + Curing Agent)
		Colours :-
		☐ Volume will vary according to colour.
ISSUANCE DATE	:	August 2017.
ORIGIN	:	Manufacture in Kuwait By GTC Paints Company Ltd.
ADDRESS	:	GTC PAINT COMPANY LTD.
		P.O.Box 24445 Safat, 13105 Safat, Kuwait
		Tel: 24710120/24710170 - Fax: 24761261.
		Email: sales @ gtcpaints. com.