GTC Paints Company Ltd.

P.O. Box: 24445 Safat - 13105 - Kuwait Sabhan Tel.: 24710120 - Fax: 24761261 Shuwaikh Tel.: 24848285 - Fax: 24837138 Capital: K.D. 1,000,000 - C.R.: 20117

FLASH POINT



شركة أصباغ جي تي سي المحدودة

ص.ب: 24445 المصفاة - 13105 - الكويت صبحان - تلفون : 24710120 - فاكس : 24761261 الشويخ - تلفون : 24848285 - فاكس : 24837138 رأس المال : 1,000,000 د.ك - س.ت : 20117

PRODUCT DESCRIPTION:

A two-pack **High Build and High Performance Poly-amide Cured Epoxy Finish Coat** developed to suit particular applications of increased thickness requirements to enhance protection characteristics in aggressive environments to allocated substrates in both New as well as Maintenance & Repair Projects.

SPEC	CIAL FEATURES	<u>:</u>						
	Excellent adhesion properties.							
	High build coat, offering increased protection in particular to steel surfaces.							
	Tough and resistant to abrasion.							
	Resistance to spillages of mild acids, alkaline solutions and sea water.							
	Surface tolerant and resistant to handling damage.							
ARE	AREA OF USES:							
	As an Internal/External finish coat over new steel / concrete substrates and previously							
	coated surfaes with Heavy Duty Coatings i.e.,							
	Concrete Structures							
	Power Stations							
	☐ Building and Architectural Works							
PRODUCT DATA:								
FINISH		:	MATT					
COLOUR		:	White & Selected Colour Range					
			Special colours are availa	_	quest			
VOLUME SOLIDS		:	46 %					
PRODUCT WEIGHT		:	1.40 kg/ltr.					
REC. FILM THICKNESS :		:	Wet: 220 microns per coat (approx. 8.7 mils) Dry: 100 microns per coat (approx. 4 mils)					
THEO. COVERAGE		:	4.6 m ² /ltr.					
	N CO VERRICE	•	Practical coverage primarily profile, method of application of			of surface		
MIXING RATIO :		Base : Curing Agent 4 : 1 (by volume)						
			Ambient Temperature	10 °C	25 °C	40 °C		
POT I	IFE	:		50 °F	77 °F	104 °F		
			No. of Hours	8 hrs.	6 hrs.	4 hrs.		
	Base : 23 °C (73 °F)							

Curing Agent : 23 °C (73 °F)

Mixed

23 °C (73 °F)

GTC Paints Company Ltd.

P.O. Box: 24445 Safat - 13105 - Kuwait Sabhan Tel.: 24710120 - Fax : 24761261 Shuwaikh Tel.: 24848285 - Fax : 24837138 Capital : K.D. 1,000,000 - C.R.: 20117



شركة أصباغ جي تي سي المحدودة

ص.ب: 24445 الصفاة - 13105 - الكويت صبحان - تلفون : 24710120 - فاكس : 24761261 الشويخ - تلفون : 24848285 - فاكس : 24837138 رأس المال : 1,000,000 د.ك - س.ت : 20117

DRYING TIME:

SUBSTRATE	TOUCH	HARD FULL CU		OVERCOATING INTERVALS		
TEMPERATURE	DRY	DRY	TIME	MINIMUM	MAXIMUM	
10 °C (50 °F)	4 hrs.	24 hrs.	10 days	30 hrs.	10 days	
25 °C (77 °F)	3 hrs.	16 hrs.	7 days	24 hrs.	7 days	
40 °C (104 °F)	1 hour	12 hrs.	5 days	16 hrs.	4 days	

STANDARDS & APPROVALS:

Supportive information is available upon request to establish an assessment to be acquired as with regards to product's compliance with/to a particular authority's queries / specifications. *Please consult with GTC Technical Service Dept.*

SURFACE PREPARATION:

- 1. Degrease areas where grease, oil and other surface contamination exist in accordance with SSPC-SP1 Solvent Cleaning. (Use *GTC002 Thinner*).
- 2. Ensure intermediate coat is dry, clean and free from dust, grease and other surface contamination.
- 3. Areas where corrosion and rusting are experienced should be prepared in accordance with Specification Requirements of **selected anti-corrosive priming / intermediate coats.**

APPLICATION DETAILS:

☐ PURPOSE OF USAGE:

Intended for a single or two coat applications over well prepared steel and concrete surfaces.

☐ MIXING & THINNING:

Material must be properly mixed and is recommended for thinning with **GTC099 Thinner** as per below table:-

Application Method	Brush/ Roller	Conv. Spray	Airless Spray
Thinning by Vol (% Max.)	10 %	15%	5 %

□ NOTES:

- ♦ For maximum performance, curing temperatures should be above 10 °C (50 °F) since material will not adequately cure below 5 °C (41 °F).
- Two pack epoxies are commonly known to chalk upon external exposure.
- ♦ It is not recommended to apply two pack epoxy material over 50 °C (122 °F)

☐ CLEANING:

For cleaning tools and equipments use GTC099 Thinner.

APPLICATION CONDITIONS:-

At a temperature ranging 5°C (41°F) to 40°C (104 °F). Relative humidity is below 75%.

GTC Paints Company Ltd.

P.O. Box: 24445 Safat - 13105 - Kuwait Sabhan Tel.: 24710120 - Fax: 24761261 Shuwaikh Tel.: 24848285 - Fax: 24837138 Capital: K.D. 1,000,000 - C.R.: 20117



شركة أصباغ جي تي سي المحدودة

ص.ب: 24445 الصفاة – 13105 – الكويت صبحان - تلفون : 24710120 – فاكس : 24761261 الشويخ - تلفون : 24848285 – فاكس : 24837138 رأس المال : 1,000,000 د.ك - س.ت : 20117

STORAGE & HANDLING:-

Product must be stored as per local regulations and should be kept in dry well ventilated location far from heat and direct sunlight. Can should be tightly closed after use. Mix well before use. Storage temperature range between 5°C (41°F) to 40°C (104 °F).

SAFETY PRECAUTIONS:

The following notes should be considered when using/applying painting material:-

- (a) Take precautions to prevent material entering the eyes (goggles should be worn, irrigate the eyes with water when become contaminated and obtain medical care at once).
- (b) Take precautions to avoid skin contact (gloves should be worn, barrier cream should be used).
- (c) Ensure that repeated contact of paint with skin is avoided.
- (d) Provide adequate ventilation. (Face masks must be worn).
- (e) Keep away from sparks and open flames (for solvent-based materials).

DISCLAIMER:

PACKING

ADDRESS

- The information given in this data sheet is for guidance only and is done to the best of our knowledge at the date of printing/issuing.
- GTC reserves the right to change the content of this data without any prior notice.
- Since we have no control over either the nature or condition of the substrate or different factors which effect the use and application of our products; therefore, no liability can be accepted on basis of this data sheet, unless we specifically agree in writing as to the suitability of the recommended product for the intended purpose; and furthermore, application of this product should be carried out under our control and direct supervision.
- Product data are subject to change without notice and become void five years from the date of issue.

White
☐ 3.6 Ltr Tins (Base + Curing Agent)
: ☐ 18 Ltr Tins (Base + Curing Agent)

Colurs

Volume will vary according to colour.

ISSUANCE DATE: August 2017

ORIGIN : Manufacture in Kuwait by GTC Paints Company Ltd.

P.O.Box 24445 Safat, 13105 Safat, Kuwait

Tel: 24710120/24710170 - Fax: 24761261.

Email: sales @ gtcpaints.com

: GTC PAINTS COMPANY LTD.