

GTC Paints Company Ltd.

P.O. Box: 24445 Safat - 13105 - Kuwait
Sabhan Tel.: 24710120 - Fax : 24761261
Shuwaikh Tel.: 24848285 - Fax : 24837138
Capital : K.D. 1,000,000 - C.R.: 20117



شركة أصباغ جى تى سى المحدودة

ص.ب: 24445 الصفاة - 13105 - الكويت
صباحان - تلفون : 24710120 - فاكس : 24761261
الشويخ - تلفون : 24848285 - فاكس : 24837138
رأس المال : 1,000,000 د.ك - س.ت : 20117

* * BESTMATT * *

PRODUCT DESCRIPTION

An economical water-borne paint , based on **Acrylic Copolymer**, developed for **Internal application only**.

SPECIAL FEATURES:

- ♦ Easy to apply; offering an economical matt appearance.
- ♦ Unsaponifiable and suitable for painting internal alkaline surfaces.
- ♦ Good colour retention.
- ♦ Good hiding power and covering capacity.
- ♦ Not recommended for external application or to areas continuously exposed to damp conditions (i.e. bathrooms) .

AREA OF USE:

As a decorative base over **Internal Walls and Ceilings**, not subjected to condensation and aggressive environmental conditions i.e.,

- ♦ Concrete
- ♦ False Ceiling
- ♦ Gypsum Board
- ♦ Brick
- ♦ Plastered Walls

PRODUCT DATA:

FINISH	:	MATT
COLOUR	:	WHITE
		Special Colours are available upon request.
VOLUME SOLIDS	:	32%
PRODUCT WEIGHT	:	1.40 Kg/ltr.
REC. FILM THICKNESS	:	Wet : 95 microns per coat (approx 3.8 mils) Dry : 30 microns per coat (approx 1.2 mil)
THEO. COVERAGE	:	10.6 m ² /ltr.
		Practical coverage primarily depends upon nature/degree of surface porosity, method of application and site conditions.
FLASH POINT	:	Non-flammable (water-borne product)

DRYING TIME:

SUBSTRATE TEMPERATURE	TOUCH DRY	HARD DRY	OVERCOATING INTERVALS	
			MINIMUM	MAXIMUM
10 °C (50 °F)	1 hour	4 hrs.	6 hrs.	IND.
25 °C (77 °F)	30 min.	3 hrs.	5 hrs.	IND.
40 °C (104 °F)	20 min	2 hrs.	4 hrs.	IND.

GTC Paints Company Ltd.

P.O. Box: 24445 Safat - 13105 - Kuwait
Sabhan Tel.: 24710120 - Fax : 24761261
Shuwaikh Tel.: 24848285 - Fax : 24837138
Capital : K.D. 1,000,000 - C.R.: 20117



شركة أصباغ جي تي سي المحدودة

ص.ب: 24445 الصفاة - 13105 - الكويت
صباحان - تلفون: 24710120 - فاكس: 24761261
الشويخ - تلفون: 24848285 - فاكس: 24837138
رأس المال: 1,000,000 د.ك - س.ت: 20117

SURFACE PREPARATION:

NEW SURFACES :

1. Degrease areas where grease, oil, soil and other surface contamination exist in accordance with **SSPC-SP1 Solvent Cleaning** . (Use **GTC002 Thinner**).
2. Wire brush/Mechanical Power Tool Clean areas where laitance, surface porosity and loosely adhering foreign material exist in accordance with **SSPC-SP2** and/or **SSPC-SP3 Standards**
3. Surfaces to be coated must be dry, clean and contamination free prior to paint application process.

OLD/PREVIOUSLY PAINTED SURFACES :-

1. Degrease areas where grease, oil and other surface contamination exist in accordance with **SSPC-SP1 Solvent Cleaning**. (Use **GTC002 Thinner**).
2. Remove all blistered, cracked and brittle paint coats off the surface.
3. Detached coats with inadequate adhesion must be properly scraped-off to a firm edge.
4. Glossy paint coatings must be sanded/roughened to ensure proper intercoat adhesion characteristics with successive paint coatings.
5. Surfaces to be coated must be dry, clean and contamination free prior to paint application process.

APPLICATION DETAILS:

☐ USAGE:

Intended for two or three finish coats application over well prepared, primed/sealed and puttied surfaces (Internally).

☐ MIXING AND THINNING:

Material must be properly mixed and is recommended for thinning with **fresh water only** as per below table:-

APPLICATION METHOD	BRUSH/ ROLLER	CONV. SPRAY	AIRLESS SPRAY
Thinning by volume (% Max.)	20%	30 %	5 %

☐ CLEANING:

For cleaning tools and equipments use **fresh water only**.

APPLICATION CONDITIONS :-

At a temperature ranging 5°C (41°F) to 40°C (104 °F) . Relative humidity is below 75%.

STORAGE & HANDLING :-

Product must be stored as per local regulations and should be kept in dry well ventilated location far from heat and direct sunlight. Can should be tightly closed after use. Mix well before use. Storage temperature range between 5°C (41°F) to 40°C (104 °F).

GTC Paints Company Ltd.

P.O. Box: 24445 Safat - 13105 - Kuwait
Sabhan Tel.: 24710120 - Fax : 24761261
Shuwaikh Tel.: 24848285 - Fax : 24837138
Capital : K.D. 1,000,000 - C.R.: 20117



شركة أصباغ جى تى سى المحدودة

ص.ب: 24445 الصفاة - 13105 - الكويت
صباحان - تلفون : 24710120 - فاكس : 24761261
الشويخ - تلفون : 24848285 - فاكس : 24837138
رأس المال : 1,000,000 د.ك - س.ت : 20117

STANDARDS & APPROVALS:

Supportive information is available upon request to establish an assessment to be acquired as with regards to product's compliance with/to a particular authority's queries /specifications. **Please consult with GTC Technical Service Dept.**

SAFETY PRECAUTIONS:

- The following notes should be considered when using/applying painting material.
- (a) Take precautions to prevent material entering the eyes (goggles should be worn, irrigate the eyes with water when become contaminated and obtain medical care at once).
 - (b) Take precautions to avoid skin contact (gloves should be worn, barrier cream should be used).
 - (c) Ensure that repeated contact of paint with skin is avoided.
 - (d) Provide adequate ventilation. (Face masks must be worn).
 - (e) Keep away from sparks and open flames (for Solvent-based material).

DISCLAIMER:

- ♦ The information given in this data sheet is for guidance only and is done to the best of our knowledge at the date of printing/issuing.
- ♦ GTC reserves the right to change the content of this data without any prior notice.
- ♦ Since we have no control over either the nature or condition of the substrate or different factors which effect the use and application of our products; therefore, no liability can be accepted on basis of this data sheet, unless we specifically agree in writing as to the suitability of the recommended product for the intended purpose; and furthermore, application of this product should be carried out under our control and direct supervision.
- ♦ Product data are subject to change without notice and become void five years from the date of issue.

PACKING : ☐ Gallon
 : ☐ 18 Ltr. Drum
ISSUANCE DATE : August 2017
ORIGIN : Manufacture in Kuwait by GTC Paints Company Ltd.
ADDRESS : **GTC PAINTS COMPANY LTD.**
 P.O.Box 24445 Safat, 13105 Safat, Kuwait
 Tel : 24710120/24710170 - Fax : 24761261 .
 Email : sales @ gtcpaints.com