

GTC Paints Company Ltd.

P.O. Box: 24445 Safat - 13105 - Kuwait
Sabhan Tel.: 24710120 - Fax : 24761261
Shuwaikh Tel.: 24848285 - Fax : 24837138
Capital : K.D. 1,000,000 - C.R.: 20117



شركة أصباغ جي تي سي المحدودة

ص.ب: 24445 الصفاة - 13105 - الكويت
صباحان - تلفون: 24710120 - فاكس: 24761261
الشويخ - تلفون: 24848285 - فاكس: 24837138
رأس المال: 1,000,000 د.ك - س.ت: 20117

* * ALKYD VARNISH * *

PRODUCT DESCRIPTION:

A high quality Clear Varnish Solution based on Long Oil Alkyd Resin intended for application over wooden surfaces.

SPECIAL FEATURES:

- ☐ Excellent flow and easy to apply.
- ☐ Good gloss retention properties.
- ☐ Provides a smooth and hard glossy finish.
- ☐ Relatively quick drying with good penetration properties.

AREA OF USES:

Mainly intended for Internal usage as decorative and protective finish/coat over wooden surfaces i.e.

- ☐ Doors
- ☐ Wood Paneling
- ☐ Wooden Frames
- ☐ Wooden Furniture

PRODUCT DATA:

| | | |
|--------------------|---|--|
| FINISH | : | Gloss |
| COLOUR | : | Clear & according to GTC Varnish Stain Colour Card Range |
| VOLUME SOLIDS | : | 42 % |
| PRODUCT WEIGHT | : | 0.9 Kg/Ltr. |
| REC.FILM THICKNESS | : | Wet : 60 microns per coat (approx 2.35 mils) Dry : 25 microns per coat (approx 1 mils) |
| THEO. COVERAGE | : | 16.8 m²/ltr. Practical coverage primarily depends upon nature/ method of application and site conditions. |
| FLASH POINT | : | Above 35°C (95 °F) |

DRYING TIME:

| SUBSTRATE TEMPERATURE | TOUCH DRY | HARD DRY | OVERCOATING INTERVALS | |
|--------------------------|--------------|-------------|-----------------------|---------|
| | | | MINIMUM | MAXIMUM |
| 10 °C (50 °F) | 4 hrs. | 18 hrs. | 24 hrs. | IND. |
| 25 °C (77 °F) | 3 hrs. | 14 hrs. | 18 hrs. | IND. |
| 40 °C (104 °F) | 2 hrs. | 8 hrs. | 14 hrs. | IND. |

STANDARDS & APPROVALS:

GTC Alkyd Varnish Clear is formulated to ASTM D-154/1985 and has been passed as suitable for usage in Kuwait by Government Laboratories and Testing Stations.

SURFACE PREPARATION:

- 1) Surfaces to be coated must be dry, clean and free from oil, grease.. etc.
- 2) Wood must not contain more that 17% moisture.
- 3) Surface must be sanded and/or ground to eliminate surface imperfections.

GTC Paints Company Ltd.

P.O. Box: 24445 Safat - 13105 - Kuwait
Sabhan Tel.: 24710120 - Fax : 24761261
Shuwaikh Tel.: 24848285 - Fax : 24837138
Capital : K.D. 1,000,000 - C.R.: 20117



شركة أصباغ جي تي سي المحدودة

ص.ب: 24445 الصفاة - 13105 - الكويت
صباحان - تلفون: 24710120 - فاكس: 24761261
الشويخ - تلفون: 24848285 - فاكس: 24837138
رأس المال: 1,000,000 د.ك - س.ت: 20117

APPLICATION DETAILS:

☐ Purpose of Usage:

Intend for a two or three coat applications over suitably prepared wooded surfaces.

☐ Mixing and Thinning:

Material must be properly mixed and is recommended for thinning with GTC002 Thinner as per below table:-

| APPLICATION METHOD | BRUSH/ ROLLER | CONV. SPRAY | AIRLESS SPRAY |
|-----------------------------|---------------|-------------|---------------|
| Thinning by volume (% Max.) | 10% | 20% | 5% |

☐ NOTE:

For best results Brush Application is recommended for first coat as this method helps achieving maximum penetration and adhesion into the substrate.

☐ CLEANING:

For cleaning tools and equipments use GTC002 Thinner.

APPLICATION CONDITIONS :-

At a temperature ranging 5°C (41°F) to 40°C (104 °F) . Relative humidity is below 75%.

STORAGE & HANDLING :-

Product must be stored as per local regulations and should be kept in dry well ventilated location far from heat and direct sunlight. Can should be tightly closed after use. Mix well before use. Storage temperature range between 5°C (41°F) to 40°C (104 °F).

SAFETY PRECAUTIONS:

The following notes should be considered when using/applying painting material:-

- Take precautions to prevent material entering the eyes (goggles should be worn, irrigate the eyes with water when become contaminated and obtain medical care at once).
- Take precautions to avoid skin contact (gloves should be worn, barrier cream should be used).
- Ensure that repeated contact of paint with skin is avoided.
- Provide adequate ventilation. (Face masks must be worn).
- Keep away from sparks and open flames (for solvent-based materials).

DISCLAIMER:

- The information given in this data sheet is for guidance only and is done to the best of our knowledge at the date of printing/issuing.
- GTC reserves the right to change the content of this data without any prior notice.
- Since we have no control over either the nature or condition of the substrate or different factors which effect the use and application of our products; therefore, no liability can be accepted on basis of this data sheet, unless we specifically agree in writing as to the suitability of the recommended product for the intended purpose; and furthermore, application of this product should be carried out under our control and direct supervision.
- Product data are subject to change without notice and become void five years from the date of issue.

PACKING

- : ☐ Gallon
- : ☐ 18 Ltr. Drum

ISSUANCE DATE

: August 2017

ORIGIN

: Manufacture in Kuwait by GTC Paints Company Ltd.

ADDRESS

: **GTC PAINTS COMPANY LTD.**

P.O.Box 24445 Safat, 13105 Safat, Kuwait

Tel : 24710120/24710170 - Fax : 24761261 .

Email : sales @ gtcpaints.com