

## GTC Paints Company Ltd.

P.O. Box: 24445 Safat - 13105 - Kuwait  
Sabhan Tel.: 24710120 - Fax : 24761261  
Shuwaikh Tel.: 24848285 - Fax : 24837138  
Capital : K.D. 1,000,000 - C.R.: 20117



## شركة أصباغ جي تي سي المحدودة

ص.ب: 24445 الصفاة - 13105 - الكويت  
صباحان - تلفون: 24710120 - فاكس: 24761261  
الشويخ - تلفون: 24848285 - فاكس: 24837138  
رأس المال: 1,000,000 د.ك - س.ت: 20117

### \*\* TENNIS COURT PAINT \*\*

#### PRODUCT DESCRIPTION:

A specially formulated Emulsion Material based on **Acrylic Resin Dispersion** incorporated with carefully selected **tough** pigments and **fillers** mainly used as a coating over substrate requiring cosmetic and protective characteristics.

#### SPECIAL FEATURES:

- ◆ Durable tough coat.
- ◆ Highly abrasion resistant.
- ◆ Smooth and washable coat.
- ◆ Excellent adhesion to most surfaces including asphalt.
- ◆ Non-bleeding properties.
- ◆ Withstands substrate movements.

#### AREA OF USE:

As a decorative and protective finish over a variety of externally exposed substrates i.e.

- ◆ Concrete Tiles
- ◆ Tennis Courts
- ◆ Car Parks
- ◆ Curb Stones
- ◆ Playgrounds
- ◆ Floor substrates

#### PRODUCT DATA:

FINISH	:	<b>EGGSHELL.</b>
COLOUR	:	<b>Green, Red and White.</b>
VOLUME SOLIDS	:	44%
PRODUCT WEIGHT	:	1.57 Kg/ltr.
REC. FILM THICKNESS	:	Wet : 120 microns per coat (approx 4.7 mils) Dry : 50 microns per coat (approx 2 mils)
THEO. COVERAGE	:	8.8 m <sup>2</sup> /ltr. Practical coverage primarily depends upon nature/degree of surface porosity, method of application and site conditions.
FLASH POINT	:	Non-flammable (water-borne product)

# GTC Paints Company Ltd.

P.O. Box: 24445 Safat - 13105 - Kuwait  
Sabhan Tel.: 24710120 - Fax : 24761261  
Shuwaikh Tel.: 24848285 - Fax : 24837138  
Capital : K.D. 1,000,000 - C.R.: 20117



# شركة أصباغ جي تي سي المحدودة

ص.ب: 24445 الصفاة - 13105 - الكويت  
صباحان - تلفون: 24710120 - فاكس: 24761261  
الشويخ - تلفون: 24848285 - فاكس: 24837138  
رأس المال: 1,000,000 د.ك - س.ت: 20117

## DRYING TIME:

SUBSTRATE TEMPERATURE	TOUCH DRY	HARD DRY	OVERCOATING INTERVALS	
			MINIMUM	MAXIMUM
10 °C (50 °F)	1½ hrs.	24 hrs.	6 hrs.	IND.
25 °C (77 °F)	1 hour	18 hrs.	4 hrs.	IND.
40 °C (104 °F)	30 min.	14 hrs.	3 hrs.	IND.

## SURFACE PREPARATION:

Surfaces must be dry and free from all contamination such as grease, oil, dirt, dust, salts, old loosely adhering powdery paint and oth friable deposits.(Meeting with SSPC-SP1,SP2,SP3 is recommended).

## APPLICATION DETAILS:

### Purpose of USAGE :

Intended for a two or three finish coats application over well prepared and cleaned surfaces.

### MIXING AND THINNING:

Material must be properly mixed and is recommended for thinning with fresh water only as per below table:-

CRITERIA	Thinning by volume % (max)		
	BRUSH/ROLLER	SPRAY	AIRLESS SPRAY
First coat	20 – 30 %	50 %	15 %
Second coat	10 – 15 %	20 – 30 %	5 %
Third coat	10 – 15 %	20 – 30 %	5 %

### METHOD OF APPLICATION :

GTC Tennis Court Paint can be applied by Brush, Roller, Spray, or Airless Spray.

### CLEANING:

For cleaning tools and equipments use **fresh water only**.

## APPLICATION CONDITIONS :-

At a temperature ranging 5°C (41°F) to 40°C (104 °F) . Relative humidity is below 75%.

## STORAGE & HANDLING :-

Product must be stored as per local regulations and should be kept in dry well ventilated location far from heat and direct sunlight. Can should be tightly closed after use. Mix well before use. Storage temperature range between 5°C (41°F) to 40°C (104 °F).

## GTC Paints Company Ltd.

P.O. Box: 24445 Safat - 13105 - Kuwait  
Sabhan Tel.: 24710120 - Fax : 24761261  
Shuwaikh Tel.: 24848285 - Fax : 24837138  
Capital : K.D. 1,000,000 - C.R.: 20117



## شركة أصباغ جي تي سي المحدودة

ص.ب: 24445 الصفاة - 13105 - الكويت  
صباحان - تلفون: 24710120 - فاكس: 24761261  
الشويخ - تلفون: 24848285 - فاكس: 24837138  
رأس المال: 1,000,000 د.ك - س.ت: 20117

### **STANDARDS & APPROVALS:**

GTC Tennis Court Paint is formulated according to KUWAIT STANDARD SPECIFICATION, modified KSS 19 & 262/1987 physical properties only and has been passed as suitable for use in Kuwait by Government Laboratories and Testing Stations.

### **SAFETY PRECAUTIONS:**

**The following notes should be considered when using/applying painting material :-**

- Take precautions to prevent material entering the eyes (goggles should be worn, irrigate the eyes with water when become contaminated and obtain medical care at once).
- Take precautions to avoid skin contact (gloves should be worn, barrier cream should be used).
- Ensure that repeated contact of paint with skin is avoided.
- Provide adequate ventilation. (Face masks must be worn).
- Keep away from sparks and open flames (for Solvent-based material).

### **DISCLAIMER:**

- ◆ The information given in this data sheet is for guidance only and is done to the best of our knowledge at the date of printing/issuing.
- ◆ GTC reserves the right to change the content of this data without any prior notice.
- ◆ Since we have no control over either the nature or condition of the substrate or different factors which effect the use and application of our products; therefore, no liability can be accepted on basis of this data sheet, unless we specifically agree in writing as to the suitability of the recommended product for the intended purpose; and furthermore, application of this product should be carried out under our control and direct supervision.
- ◆ Product data are subject to change without notice and become void five years from the date of issue.

**PACKING** : ◆ Gallon  
: ◆ 18 Ltr. Drum  
**ISSUANCE DATE** : August 2017  
**ORIGIN** : Manufacture in Kuwait by GTC Paints Company Ltd.  
**ADDRESS** : **GTC PAINTS COMPANY LTD.**  
P.O.Box 24445 Safat, 13105 Safat, Kuwait  
Tel : 24710120/24710170 - Fax : 24761261 .  
Email : sales @ gtcpaints.com