

# GTC Paints Company Ltd.

P.O. Box: 24445 Safat - 13105 - Kuwait  
Sabhan Tel.: 24710120 - Fax : 24761261  
Shuwaikh Tel.: 24848285 - Fax : 24837138  
Capital : K.D. 1,000,000 - C.R.: 20117



# شركة أصباغ جى تى سى المحدودة

ص.ب: 24445 الصفاة - 13105 - الكويت  
صباحان - تلفون : 24710120 - فاكس : 24761261  
الشويخ - تلفون : 24848285 - فاكس : 24837138  
رأس المال : 1,000,000 د.ك - س.ت : 20117

## **\*\* E.L. FIRENZE \*\***

### EXTERME LINE COATING

#### **PRODUCT DESCRIPTION :**

GTC Technique E.L. Firenze are pastes offering a multitude of aesthetically pleasing effects which impart a rich luxurious quality touch to the locality. It is also protective as well as decorative for interior and exterior surfaces. GTC Technique E.L. Firenze is water and weather resistant, flexible and very durable.

**MONOCHROMATIC :** On rubbing will produce one colour with shaded areas.

#### **PRODUCT DETAILS :**

##### **FINISHES :**

**FIRENZE STD.**

Sandy mono-colour finish shaded by rubbing.

#### **SPECIAL FEATURES:**

- Exterior, Interior use.
- Unique decorative effects.
- Flexible (Bridges hairline cracks).
- Water resistant.
- Excellent durability.
- Easy application.

#### **AREA OF USE:**

As a decorative and protective Exterior / Interior structured coat over new and old building surfaces i.e.,

- ♦ Interior ceilings of concrete and plastered walls.
- ♦ Gypsum Board.
- ♦ Concrete, GRC blocks.
- ♦ Wooden Surfaces.
- ♦ Block works, brick works, stone..... etc.

#### **PRODUCT DATA :**

FINISH	: Sandy Matt .
VOLOUME SOLIDS	: 63 % .
PRODUCT WEIGHT	: 1.6 kg./ltr.
FILM THICKNESS	: 1 mm. (2 coats)
THEORETICAL COVERAGE	: 0.75 kg./m <sup>2</sup> (Per 2 coats)
	Practical coverage primarily depends upon nature/degree of surface porosity, method of application and site conditions.
FLASH POINT	: Non-flammable (water-borne product)

# GTC Paints Company Ltd.

P.O. Box: 24445 Safat - 13105 - Kuwait  
Sabhan Tel.: 24710120 - Fax : 24761261  
Shuwaikh Tel.: 24848285 - Fax : 24837138  
Capital : K.D. 1,000,000 - C.R.: 20117



# شركة أصباغ جي تي سي المحدودة

ص.ب: 24445 الصفاة - 13105 - الكويت  
صباحان - تلفون: 24710120 - فاكس: 24761261  
الشويخ - تلفون: 24848285 - فاكس: 24837138  
رأس المال: 1,000,000 د.ك - س.ت: 20117

## SURFACE PREPARATION:

### NEW SURFACE :

1. Degrease areas where grease, oil, soil and other surface contamination exist in accordance with **SSPC-SP1 Solvent Cleaning** . (Use **GTC002 Thinner**).
2. Wire Brush/Mechanical Power Tool Clean Concrete areas where laitance, surface porosity and loosely adhering foreign material exist in accordance with **SSPC-SP2** and/or **SSPC-SP3 Standards**
3. Surfaces to be coated must be dry, clean and contamination free prior to paint application process.

### OLD/PREVIOUSLY PAINTED SURFACES :

1. Degrease areas where grease, oil and other surface contamination exist in accordance with **SSPC-SP1 Solvent Cleaning**. (Use **GTC002 Thinner**).
2. Remove all blistered, cracked and brittle paint coats off the surface.
3. Coats with inadequate adhesion must be properly scraped-off to a firm edge.
4. Glossy paint coatings must be sanded/roughened to ensure proper inter coat adhesion characteristics with successive paint coatings.
5. Surfaces to be coated must be dry, clean and contamination free prior to paint application process.

## APPLICATION DETAILS:

**Note:** This Product is decorative technique material and should be applied by experienced trained applicators. The final appearance depends on their skills and dexterity.

## RECOMMENDED PRIMER/SEALER:

1. GTC Acrylic Sealer (thinned 50-100% by volume with fresh water).
2. GTC Textured Primer (thinned 25% by volume with fresh water)  
(Refer to individual data sheet for additional information).
3. GTC P.Synthetic Sealer (thinned 25% by volume with GTC002 Thinner)

## METHOD OF APPLICATION:

### **ROUGH : FIRENZE Std. (1 Colour):-**

- Apply one coat at the required thickness with a trowel in a uniform thickness and leave to dry completely.
- Apply patches on dried film surface to produce required appearance.
- Apply second coat in the same manner as finish coat to have smooth finish , or as patches to produce required finish appearance.

### **Note:**

- 1) Polishing with steel spatula or mechanical buffing will increase the sheen.
- 2) If required a light coat of protective material may be applied after complete drying of **Frenze..**
- 3) It is very important to note that any applicator should be experienced with decorative **Frenze..**
- 4) Colours of pastes may vary due to technical reasons therefore trials prior to commencing jobs should be done.

## APPLICATION CONDITIONS :-

At a temperature ranging 5°C (41°F) to 40°C (104 °F) . Relative humidity is below 75%.

## STORAGE & HANDLING :-

Product must be stored as per local regulations and should be kept in dry well ventilated location far from heat and direct sunlight. Can should be tightly closed after use. Mix well before use. Storage temperature range between 5°C (41°F) to 40°C (104 °F).

## GTC Paints Company Ltd.

P.O. Box: 24445 Safat - 13105 - Kuwait  
Sabhan Tel.: 24710120 - Fax : 24761261  
Shuwaikh Tel.: 24848285 - Fax : 24837138  
Capital : K.D. 1,000,000 - C.R.: 20117



## شركة أصباغ جي تي سي المحدودة

ص.ب: 24445 الصفاة - 13105 - الكويت  
صباحان - تلفون : 24710120 - فاكس : 24761261  
الشويخ - تلفون : 24848285 - فاكس : 24837138  
رأس المال : 1,000,000 د.ك - س.ت : 20117

### SAFETY PRECAUTIONS :

The following notes should be considered when using/applying painting material:-

- (a) Take precautions to prevent material entering the eyes (goggles should be worn, irrigate the eyes with water when become contaminated and obtain medical care at once).
- (b) Take precautions to avoid skin contact (gloves should be worn, barrier cream should be used).
- (c) Ensure that repeated contact of paint with skin is avoided.
- (d) Provide adequate ventilation. (Face masks must be worn).
- (e) Keep away from sparks and open flames (for solvent-based materials).

### DISCLAIMER:

- ♦ The information given in this data sheet is for guidance only and is done to the best of our knowledge at the date of printing/issuing.
- ♦ GTC reserves the right to change the content of this data without any prior notice.
- ♦ Since we have no control over either the nature or condition of the substrate or different factors which effect the use and application of our products; therefore, no liability can be accepted on basis of this data sheet, unless we specifically agree in writing as to the suitability of the recommended product for the intended purpose; and furthermore, application of this product should be carried out under our control and direct supervision.
- ♦ Product data are subject to change without notice and become void five years from the date of issue.

PACKING	:	□ 25 KG Drum.
ISSUANCE DATE	:	August 2017.
ORIGIN	:	Manufacture in Kuwait By GTC Paints Company Ltd.
ADDRESS	:	GTC PAINTS COMPANY LTD. P.O.BOX 24445 Safat, 13105 Safat, Kuwait. Tel : 24710120/24710170 - Fax : 24761261. Email : sales @ gtcpaints.com .