

## GTC Paints Company Ltd.

P.O. Box: 24445 Safat - 13105 - Kuwait  
Sabhan Tel.: 24710120 - Fax : 24761261  
Shuwaikh Tel.: 24848285 - Fax : 24837138  
Capital : K.D. 1,000,000 - C.R.: 20117



## شركة أصباغ جى تى سى المحدودة

ص.ب: 24445 الصفاة - 13105 - الكويت  
صباحان - تلفون: 24710120 - فاكس: 24761261  
الشويخ - تلفون: 24848285 - فاكس: 24837138  
رأس المال: 1,000,000 د.ك - س.ت: 20117

### \* \* WHITE PRIMER \* \*

#### PRODUCT DESCRIPTION:

An economical and pigmented water-borne primer/sealer coat based on acrylic copolymer intended for sealing porous surfaces and provide a key for subsequent conventional coats.

#### SPECIAL FEATURES:

- ☐ Easy to apply with good penetration properties.
- ☐ Resistant to fungul and mould growth/attack.
- ☐ Suitable for application over alkaline surfaces.
- ☐ Water vapour permeable coat.
- ☐ Good dying properties.

#### AREA OF USES

As a primer/sealer coat over interior walls and ceilings, not subjected to condensation i.e.,

- ☐ Concrete Structure
- ☐ GRC Blocks
- ☐ Gypsum Board
- ☐ Fairface Concrete
- ☐ New & Old Plaster

#### PRODUCT DATA:

FINISH	:	<b>EGG SHELL</b>
COLOUR	:	White
VOLUME SOLID	:	15 %
PRODUCT WEIGHT	:	1.1 Kg/ltr.
RECOMMENDED		Wet: 100 microns per coat (approx 4 mils)
FILM THICKNESS	:	Dry: 15 microns per coat (approx 0.6 mil)
THEORETICAL	:	10 m <sup>2</sup> /ltr.
COVERAGE		Practical coverage primarily depends on nature/degree of surface porosity, method of application and site conditions.
FLASH POINT	:	Non-flammable (water-borne product)

#### DRYING TIME:

SUBSTRATE TEMPERATURE	TOUCH DRY	HARD DRY	OVERCOATING MINIMUM	INTERVALS MAXIMUM
10 °C (50 °F)	1 hour	4 hrs.	6 hrs.	IND.
25 °C (77 °F)	30 min.	3 hrs.	5 hrs.	IND.
40 °C (104 °F)	20 min.	2 hrs.	4 hrs.	IND.

# GTC Paints Company Ltd.

P.O. Box: 24445 Safat - 13105 - Kuwait  
Sabhan Tel.: 24710120 - Fax : 24761261  
Shuwaikh Tel.: 24848285 - Fax : 24837138  
Capital : K.D. 1,000,000 - C.R.: 20117



## شركة أصباغ جي تي سي المحدودة

ص.ب: 24445 الصفاة - 13105 - الكويت  
صباحان - تلفون : 24710120 - فاكس : 24761261  
الشويخ - تلفون : 24848285 - فاكس : 24837138  
رأس المال : 1,000,000 د.ك - س.ت : 20117

### SURFACE PREPARATION:

#### New Surfaces :-

1. Degrease areas where grease, oil and other surface contamination exist. Solvent washing is recommended. (Use **GTC002 Thinner**).
2. Wire brush/Mechanical Power Tool to roughen areas where laitance, surface porosity and loosely adhering foreign material exist.
3. Surfaces to be coated must be dry, clean and dust free prior to paint application process.

#### OLD/PREVIOUSLY PAINTED SURFACES :

1. Degrease areas where grease, oil and other surface contamination exist. Solvent washing is recommended. (Use **GTC002 Thinner**).
2. Remove all blistered, cracked and brittle paint coats off the surface.
3. Detached coats with inadequate adhesion must be firmly scrapped off.
4. Glossy paint coatings must be sanded/roughened to ensure proper intercoat adhesion.
5. Surfaces to be coated must be dry, clean and dust free prior to paint application process.

### APPLICATION DETAILS:

- ☐ Purpose of Usage of Primer Sealer :  
Intended for a single coat application over well prepared Internal/External surfaces.
- ☐ Mixing and thinning:  
Material must be properly mixed and thinned 2-3 times by volume with fresh water only.
- ☐ Method of Application:  
**GTC Primer Sealer** can be applied by brush, roller, conventional and airless spray.
- ☐ Note:  
(1) For best results over porous surfaces brush application is recommended as this method helps achieving maximum penetration and adhesion into the substrate.  
(2) This product can be overcoated with all types of oil or water based paint and putty.

#### ☐ CLEANING:

For cleaning tools and equipments use **fresh water** only.

### APPLICATION CONDITIONS :-

At a temperature ranging 5°C (41°F) to 40°C (104 °F) . Relative humidity is below 75%.

### STORAGE & HANDLING :-

Product must be stored as per local regulations and should be kept in dry well ventilated location far from heat and direct sunlight. Can should be tightly closed after use. Mix well before use. Storage temperature range between 5°C (41°F) to 40°C (104 °F).

# GTC Paints Company Ltd.

P.O. Box: 24445 Safat - 13105 - Kuwait  
Sabhan Tel.: 24710120 - Fax : 24761261  
Shuwaikh Tel.: 24848285 - Fax : 24837138  
Capital : K.D. 1,000,000 - C.R.: 20117



# شركة أصباغ جي تي سي المحدودة

ص.ب: 24445 الصفاة - 13105 - الكويت  
صباحان - تلفون : 24710120 - فاكس : 24761261  
الشويخ - تلفون : 24848285 - فاكس : 24837138  
رأس المال : 1,000,000 د.ك - س.ت : 20117

## STANDARDS & APPROVALS:

Supportive information is available upon request to establish an assessment to be acquired as with regards to product's compliance with/to a particular authority's queries /specifications. **Please consult with GTC Technical Service Dept.**

## SAFETY PRECAUTIONS:

The following notes should be considered when using/applying painting material:-

- Take precautions to prevent material entering the eyes (goggles should be worn, irrigate the eyes with water when become contaminated and obtain medical care at once).
- Take precautions to avoid skin contact (gloves should be worn, barrier cream should be used).
- Ensure that repeated contact of paint with skin is avoided.
- Provide adequate ventilation.
- Keep away from sparks and open flames (for solvent-based materials).

## DISCLAIMER:

- ◆ The information given in this data sheet is for guidance only and is done to the best of our knowledge at the date of printing/issuing.
- ◆ GTC reserves the right to change the content of this data without any prior notice.
- ◆ Since we have no control over either the nature or condition of the substrate or different factors which effect the use and application of our products; therefore, no liability can be accepted on basis of this data sheet, unless we specifically agree in writing as to the suitability of the recommended product for the intended purpose; and furthermore, application of this product should be carried out under our control and direct supervision.
- ◆ Product data are subject to change without notice and become void five years from the date of issue.

**PACKING** : ☐ Gallon  
                  : ☐ 18 Ltr. Drum  
**ISSUANCE DATE** : August 2017  
**ORIGIN** : Manufacture in Kuwait by GTC Paints Company Ltd.  
**ADDRESS** : **GTC PAINTS COMPANY LTD.**  
                  P.O.Box 24445 Safat, 13105 Safat, Kuwait  
                  Tel : 24710120/24710170 - Fax : 24761261 .  
                  Email : sales @ gtcpaints.com