

GTC Paints Company Ltd.

P.O. Box: 24445 Safat - 13105 - Kuwait
Sabhan Tel.: 24710120 - Fax : 24761261
Shuwaikh Tel.: 24848285 - Fax : 24837138
Capital : K.D. 1,000,000 - C.R.: 20117



شركة أصباغ جي تي سي المحدودة

ص.ب: 24445 الصفاة - 13105 - الكويت
صباحان - تلفون : 24710120 - فاكس : 24761261
الشويخ - تلفون : 24848285 - فاكس : 24837138
رأس المال : 1,000,000 د.ك - س.ت : 20117

* * ROLLTEX PAINT * *

PRODUCT DESCRIPTION:

A durable textured finish paint based on Acrylic Copolymer reinforced with High Quality Aggregates, developed to provide a durable hard decorative finish with the following features:

SPECIAL FEATURES:

- ◆ Excellent exterior durability.
- ◆ Good water and weather resistance.
- ◆ Hard yet flexible film.
- ◆ Ready for use and easy to apply.
- ◆ Minimize minor surface imperfections.
- ◆ Very good adhesion and low maintenance requirements.
- ◆ Suitable for application over alkaline surfaces.
- ◆ Available in fine, medium and heavy textures applicable by various methods to give a selective pleasant decorative finish.

AREA OF USE:

As an Interior/Exterior decorative and protective coat over new and old surfaces i.e.,

- ◆ Concrete
- ◆ Plastered walls
- ◆ Gypsum Boards
- ◆ Cement
- ◆ Fencing
- ◆ Block work, Brick Work
- ◆ Woden surfaces (i.e., portable/pre-fabricated houses).

PRODUCT DATA:

FINISH : **TEXTURED** (Fine, Medium, Heavy) **MATT**
COLOUR : **WHITE .**

CRITERIA	FINE	MEDIUM	HEAVY
VOLUME SOLIDS	53%	66%	68%
PRODUCT WEIGHT	1.60 kg/ltr.	1.81 kg/ltr.	1.87 kg/ltr.
RECOMMENDED DFT (Approx.)	0.25-0.5 MM	0.5-1 MM	1.5-2 MM
THEORETICAL COVERAGE	0.5 kg/m ²	0.75-1 kg/m ²	1-1.5 kg/m ²
FLASH POINT	Non-Flammable (water-borne product)	Non-Flammable (water-borne product)	Non-Flammable (water-borne product)

Note: Practical coverage primarily depends upon nature of the surface, degree of surface porosity/roughness, method of application skill of paint applicator and site conditions.

DRYING TIME:

SUBSTRATE TEMPERATURE	TOUCH DRY	HARD DRY	OVERCOATING INTERVALS	
			MINIMUM	MAXIMUM
10 °C (50 °F)	1½ hr.	6 hrs.	10 hrs.	IND.
25 °C (77 °F)	1 hour	5 hrs.	8 hrs.	IND.
40 °C (104 °F)	30 min.	4 hrs.	6 hrs.	IND.

GTC Paints Company Ltd.

P.O. Box: 24445 Safat - 13105 - Kuwait
Sabhan Tel.: 24710120 - Fax : 24761261
Shuwaikh Tel.: 24848285 - Fax : 24837138
Capital : K.D. 1,000,000 - C.R.: 20117



شركة أصباغ جي تي سي المحدودة

ص.ب: 24445 الصفاة - 13105 - الكويت
صباحان - تلفون: 24710120 - فاكس: 24761261
الشويخ - تلفون: 24848285 - فاكس: 24837138
رأس المال: 1,000,000 د.ك - س.ت: 20117

SURFACE PREPARATION:

NEW SURFACES :

1. Degrease areas where grease, oil, soil and other surface contamination exist in accordance with **SSPC-SP1 Solvent Cleaning** . (Use **GTC002 Thinner**).
2. Wire Brush/Mechanical Power Tool Clean areas where laitance, surface porosity and loosely adhering foreign material exist in accordance with **SSPC-SP2** and/or **SSPC-SP3 Standards**
3. Surfaces to be coated must be dry, clean and contamination free prior to paint application process.

OLD/PREVIOUSLY PAINTED SURFACES :

1. Degrease areas where grease, oil and other surface contamination exist in accordance with **SSPC-SP1 Solvent Cleaning**. (Use **GTC002 Thinner**).
2. Remove all blistered, cracked and brittle paint coats off the surface.
3. Detached coats with inadequate adhesion must be properly scraped-off to a firm edge.
4. Glossy paint coatings must be sanded/roughened to ensure proper intercoat adhesion characteristics with successive paint coatings.
5. Surfaces to be coated must be dry, clean and contamination free prior to paint application process.

APPLICATION DETAILS:

◆ MIXING:

Rolltex Paint must be properly mixed before use.

◆ THINNING:

Not recommended. If necessary thin with **GTC Acrylic Sealer** (Max. 5% by volume).

◆ SYSTEM:

Intended for a **single coat application** using Perforated Roller over well prepared, primed and undercoated surfaces as follows:-

☐ RECOMMENDED PRIMER/SEALER:

1. GTC Acrylic Sealer (thinned 50-100% by volume with fresh water).
2. GTC Textured Primer (thinned 25% by volume with fresh water)
(Refer to individual data sheet for additional information).
3. GTC P.Synthetic Sealer (thinned 25% by volume with GTC002 Thinner)

◆ NOTE:

Due to severe dust conditions in Kuwait, this product will retain dust and dirt causing is discoloured appearance; therefore, in order to overcome the discolouring problem and also to enhance product properties, it is recommended to apply a protective/decorative coat of the following:-

- A. Getathane Recoatable Polyurethane Gloss or Matt Finish (White or selective colours).
- B. GTC Acrylic Guard Paint (White or selective colours) .
- C. Getashine Acrylic Emulsion Paint (White or selective colours).

◆ CLEANING:

For cleaning tools and equipments use **fresh water only**.

APPLICATION CONDITIONS :-

At a temperature ranging 5°C (41°F) to 40°C (104 °F) . Relative humidity is below 75%.

STORAGE & HANDLING :-

Product must be stored as per local regulations and should be kept in dry well ventilated location far from heat and direct sunlight. Can should be tightly closed after use. Mix well before use. Storage temperature range between 5°C (41°F) to 40°C (104 °F).

GTC Paints Company Ltd.

P.O. Box: 24445 Safat - 13105 - Kuwait
Sabhan Tel.: 24710120 - Fax : 24761261
Shuwaikh Tel.: 24848285 - Fax : 24837138
Capital : K.D. 1,000,000 - C.R.: 20117



شركة أصباغ جي تي سي المحدودة

ص.ب: 24445 الصفاة - 13105 - الكويت
صباحان - تلفون: 24710120 - فاكس: 24761261
الشويخ - تلفون: 24848285 - فاكس: 24837138
رأس المال: 1,000,000 د.ك - س.ت: 20117

STANDARDS & APPROVALS:-

GTC Rolltex Paint is formulated according to FEDERAL SPECIFICATION TTC 555B and has been passed as suitable for use in Kuwait by Government Laboratories and Testing Stations.

SAFETY PRECAUTIONS:

The following notes should be considered when using/applying painting material:-

- Take precautions to prevent material entering the eyes (goggles should be worn, irrigate the eyes with water when become contaminated and obtain medical care at once).
- Take precautions to avoid skin contact (gloves should be worn, barrier cream should be used).
- Ensure that repeated contact of paint with skin is avoided.
- Provide adequate ventilation. (Face masks must be worn).
- Keep away from sparks and open flames (for solvent-based materials).

DISCLAIMER:

- ♦ The information given in this data sheet is for guidance only and is done to the best of our knowledge at the date of printing/issuing.
- ♦ GTC reserves the right to change the content of this data without any prior notice.
- ♦ Since we have no control over either the nature or condition of the substrate or different factors which effect the use and application of our products; therefore, no liability can be accepted on basis of this data sheet, unless we specifically agree in writing as to the suitability of the recommended product for the intended purpose; and furthermore, application of this product should be carried out under our control and direct supervision.
- ♦ Product data are subject to change without notice and become void five years from the date of issue.

PACKING : 25 Kg Drum
ISSUANCE DATE : August 2017.
ORIGIN : Manufacture in Kuwait By GTC Paints Company Ltd.
ADDRESS : GTC PAINTS COMPANY
P. O. Box 24445 Safat, 13105 Safat, Kuwait
Tel. 24710120/24710170 Fax No. 24761261
Email : sales @ gtcpaints.com