

GTC Paints Company Ltd.

P.O. Box: 24445 Safat - 13105 - Kuwait
Sabhan Tel.: 24710120 - Fax : 24761261
Shuwaikh Tel.: 24848285 - Fax : 24837138
Capital : K.D. 1,000,000 - C.R.: 20117



شركة أصباغ جى تى سى المحدودة

ص.ب: 24445 الصفاة - 13105 - الكويت
صباحان - تلفون : 24710120 - فاكس : 24761261
الشويخ - تلفون : 24848285 - فاكس : 24837138
رأس المال : 1,000,000 د.ك - س.ت : 20117

* * UNDERCOAT * *

PRODUCT DESCRIPTION :

A Superior quality Thixotropic and Alkyd based intermediate coat formulated as an obliteration Coat over suitably primed surfaces.

SPECIAL FEATURES:

- ☐ Very high build power.
- ☐ Easy to apply offering a smooth and flat finish.
- ☐ Relatively quick drying.
- ☐ Due to its balanced pigments, GTC Undercoat offers maximum Enamel holdout.

AREA OF USES:

As an Intermediate Coat on Exterior/Interior concrete, masonry, steel and wooden surfaces, i.e.,

- ☐ Interior Walls/Exterior Concrete Facades and fronts.
- ☐ Steel and wooden Doors, Frames...etc..
- ☐ Surfaces to be finished/overcoated with conventional oil Paints(Gloss or Flat Finished) as well as water based paints.

PRODUCT DATA :

FINISH	:	MATT.
COLOUR	:	White&Light Shade Colours upon request .
VOLUME SOLIDS	:	54 % .
PRODUCT WEIGHT	:	1.40 kg/ltr.
REC. FILM THICKNESS	:	Wet : 70 microns per coat (approx.2.8 mils) Dry : 35 microns per coat (approx 1.4 mils)
THEO. COVERAGE	:	15.4 m ² /ltr Practical coverage primarily depends upon nature/degree of surface porosity, method of application and site conditions.
FLASH POINT	:	Above 35 °C (95 °F).

DRYING TIME:

SUBSTRATE TEMPERATURE	TOUCH DRY	HARD DRY	OVERCOATING INTERVALS	
			MINIMUM	MAXIMUM
10 °C (50 °F)	5 hrs.	36 hrs.	24 hrs.	IND.
25 °C (77 °F)	4 hrs	24 hrs.	24 hrs.	IND.
40 °C (104 °F)	3 hrs	18 hrs.	24 hrs.	IND.

SURFACE PREPARATION :-

Surface to be coated i.e. Masonry,Steel,Wood...etc,should be properly prepared and suitably primed with required primer as per information provided in individual data sheets depending upon surface type/nature...etc (Please refer to Getascheme Coating Sequence).

GTC Paints Company Ltd.

P.O. Box: 24445 Safat - 13105 - Kuwait
Sabhan Tel.: 24710120 - Fax : 24761261
Shuwaikh Tel.: 24848285 - Fax : 24837138
Capital : K.D. 1,000,000 - C.R.: 20117



شركة أصباغ جي تي سي المحدودة

ص.ب: 24445 الصفاة - 13105 - الكويت
صباحان - تلفون : 24710120 - فاكس : 24761261
الشويخ - تلفون : 24848285 - فاكس : 24837138
رأس المال : 1,000,000 د.ك - س.ت : 20117

APPLICATION DETAILS:

□ Purpose of Usage:

Intended for a single intermediate coat application and to be overcoated with two or three coats of GTC Conventional Oil and/or Water Based Paints.

□ Mixing and Thinning:

Material must be properly mixed and is recommended for thinning with GTC002 Thinner as per below table:-

APPLICATION METHOD	BRUSH/ROLLER	CONV.SPRAY	AIRLESS SPRAY
Thinning by volume(% max.)	10 %	15 %	5 %

□ Cleaning :

For cleaning tools and equipments use GTC002 Thinner.

APPLICATION CONDITIONS :-

At a temperature ranging 5°C (41°F) to 40°C (104 °F) . Relative humidity is below 75%.

STORAGE & HANDLING :-

Product must be stored as per local regulations and should be kept in dry well ventilated location far from heat and direct sunlight. Can should be tightly closed after use. Mix well before use. Storage temperature range between 5°C (41°F) to 40°C (104 °F).

SAFETY PRECAUTIONS:

The following notes should be considered when using/applying painting material:-

- Take precautions to prevent material entering the eyes (goggles should be worn, irrigate the eyes with water when become contaminated and obtain medical care at once).
- Take precautions to avoid skin contact (gloves should be worn, barrier cream should be used).
- Ensure that repeated contact of paint with skin is avoided.
- Provide adequate ventilation. (Face masks must be worn).
- Keep away from sparks and open flames (for solvent-based materials).

DISCLAIMER:

- The information given in this data sheet is for guidance only and is done to the best of our knowledge at the date of printing/issuing.
- GTC reserves the right to change the content of this data without any prior notice.
- Since we have no control over either the nature or condition of the substrate or different factors which effect the use and application of our products; therefore, no liability can be accepted on basis of this data sheet, unless we specifically agree in writing as to the suitability of the recommended product for the intended purpose; and furthermore, application of this product should be carried out under our control and direct supervision.
- Product data are subject to change without notice and become void five years from the date of issue.

PACKING : □ Gallon

: □ 18 Ltr. Drum

ISSUANCE DATE : August 2017 .

ORIGIN : Manufacture in Kuwait by GTC Paints Company Ltd.

ADDRESS : GTC PAINTS COMPANY LTD.

P.O.Box 24445 Safat, 13105 Safat, Kuwait

Tel : 24710120/24710170 - Fax : 24761261 .

Email : sales @ gtcpaints .com