GTC Paints Company Ltd.

P.O. Box: 24445 Safat - 13105 - Kuwait Sabhan Tel.: 24710120 - Fax: 24761261 Shuwaikh Tel.: 24848285 - Fax: 24837138 Capital: K.D. 1,000,000 - C.R.: 20117



شركة أصباغ جي تي سي المحدودة

ص.ب: 24445 الصفاة - 13105 - الكويت صبحان - تلفون : 24710120 - فاكس : 24761261 الشويخ - تلفون : 24848285 - فاكس : 24837138 رأس المال : 1,000,000 د.ك - س.ت : 20117

** ACRYLIC PUTTY **

PRODUCT DESCRIPTION:

A good quality water-borne Interior Wall Putty based on Acrylic Copolymer blended with carefully selected pigments and extenders; formulated to match the speed of modern building construction in the Architectural Industry.

SPECIAL FEATUR	ES:-			
☐ Dries to form a seconventional para ☐ Does not shrink ☐ Non-toxic & nor ☐ Very good hidin	d provides a surface tole ints. or crack. n-flammabl ag power; p	a smooth surface / finish. erant and compatible with substrates with all types of		
AREA OF USE: As an Interior levelling: Concrete structu	_	naterial over a variety of new and old substrates i.e., Fairface concrete		
PRODUCT DATA	*			
FINISH	:	MATT		
COLOUR	:	White to off-white		
VOLUME SOLID	:	46%		
PRODUCT WEIGHT	:	1.6 1.8kg/ltr.		
REC. FILM THICKNE	SS :	Up to 400 microns per application		
THEO. COVERAGE	:	approx. 2.0 m ² /kg. depending upon applied thickness		
		Practical coverage primarily depends upon nature/degree of		
		surface porosity, method of application and site conditions.		
FLASH POINT	:	Non-flammable (water-borne product)		

GTC Paints Company Ltd.

P.O. Box: 24445 Safat - 13105 - Kuwait Sabhan Tel.: 24710120 - Fax: 24761261 Shuwaikh Tel.: 24848285 - Fax: 24837138 Capital: K.D. 1,000,000 - C.R.: 20117



شركة أصباغ جي تي سي المحدودة

ص.ب: 24445 الصفاة - 13105 - الكويت صبحان - تلفون : 24710120 - فاكس : 24761261 الشويخ - تلفون : 24848285 - فاكس : 24837138 رأس المال : 1,000,000 د.ك - س.ت : 20117

DRYING TIME:

SUBSTRATE	TOUCH	HARD	OVERCOATING INTERVALS	
TEMPERATURE	DRY	DRY	MINIMUM *	MAXIMUM
10 °C (50 °F)	1 hour	12 hrs.	10 hrs.	IND.
25 °C (77 °F)	45 min.	8 hrs.	6 hrs.	IND.
40°C (104 °F)	30 min.	4 hrs.	4 hrs.	IND.

Notes: * Allow 6 hours before applying water based paints.

SURFACE PREPARATION:

All surfaces must be clean, dry and free from dust, oil, grease, mould, mildew or loosely adhering materials . . . etc.

APPLICATION DETAILS:

	USA	GE:				
(A)	Inten	ded for two or three coat applications over suitably sealed/primed surfaces (Internally).				
	MIXING AND THINNING:					
	Mat	erial is ready for use; no thinning is required.				
	METHOD OF APPLICATION:					
	GTC	Acrylic Putty can be applied by hand trowel, putty knife and steel scraper.				
	NOTES:					
		Apply the putty material in successive thin layers. Sanding is to be carried between layers after a minimum of 5 - 6 hrs. to achieve perfect smoothness and adhesion.				
		Do not exceed Recommended Film Thickness as this will result in poor adhesion, cracking and weakening of the applied painting system. It is recommended to remove old paint layers before application of GTC Acrylic Putty. (Glossy surfaces should be roughened until gloss fades away).				
		CLEANING:				
	For	cleaning tools and equipments use fresh water only.				

APPLICATION CONDITIONS:-

At a temperature ranging 5°C (41°F) to 40°C (104 °F). Relative humidity is below 75%.

STORAGE & HANDLING :-

Product must be stored as per local regulations and should be kept in dry well ventilated location far from heat and direct sunlight. Can should be tightly closed after use. Mix well before use. Storage temperature range between 5°C (41°F) to 40°C (104 °F).

^{*} If oil solvent based paints to be used extend the overcoating time to 24 hrs.

GTC Paints Company Ltd.

P.O. Box: 24445 Safat - 13105 - Kuwait Sabhan Tel.: 24710120 - Fax: 24761261 Shuwaikh Tel.: 24848285 - Fax: 24837138 Capital: K.D. 1,000,000 - C.R.: 20117



شركة أصباغ جي تي سي المحدودة

ص.ب: 24445 الصفاة - 13105 - الكويت صبحان - تلفون : 24710120 - فاكس : 24761261 الشويخ - تلفون : 24848285 - فاكس : 24837138 رأس المال : 1,000,000 د.ك - س.ت : 20117

STANDARDS & APPROVALS:

GTC Acrylic Putty is formulated to Kuwait Standard Specification K.S.S. No. 850/1996 and has been passed as suitable for usage as a wall putty in Kuwait by the Government Laboratories and Testing Stations.

SAFETY PRECAUTIONS:

The following notes should be considered when using/applying material:-

- (a) Take precautions to prevent material entering the eyes (goggles should be worn, irrigate the eyes with water when become contaminated and obtain medical care at one).
- (b) Take precautions to avoid skin contact (gloves should be worn, barrier cream should be used).
- (c) Ensure that repeated contact of paint with skin is avoided.
- (d) Provide adequate ventilation. (Face masks must be worn).
- (e) Keep away from sparks and open flames (for solvent-based materials).

DISCLAIMER:

- The information given in this data sheet is for guidance only and is done to the best of our knowledge at the date
 of printing/issuing.
- GTC reserves the right to change the content of this data without any prior notice.
- Since we have no control over either the nature or condition of the substrate or different factors which affect the use and application of our products; therefore, no liability can be accepted on basis of this data sheet, unless we specifically agree in writing from us as to the suitability of the recommended product for the intended purpose; and furthermore, application of this product should be carried out under our control and direct supervision.
- Product data are subject to change without notice and become void five years from the date of issue.

PACKING : • 1 Kg Plastic Tins

• 5 kg Gallons

• 25 kg Drum/Nylon Bag.

ISSUANCE DATE : August 2017.

ORIGIN : Manufacture in Kuwait By GTC Paints Company Ltd.

ADDRESS : GTC PAINTS COMPANY LTD.
P. O. Box 24445 Safat, 13105 Safat, Kuwait

Tel: 24710120/24710170 - Fax: 24761261.

Email: sales @ gtcpaints.com