

GTC Paints Company Ltd.

P.O. Box: 24445 Safat - 13105 - Kuwait
Sabhan Tel.: 24710120 - Fax : 24761261
Shuwaikh Tel.: 24848285 - Fax : 24837138
Capital : K.D. 1,000,000 - C.R.: 20117



شركة أصباغ جي تي سي المحدودة

ص.ب: 24445 الصفاة - 13105 - الكويت
صباحان - تلفون: 24710120 - فاكس: 24761261
الشويخ - تلفون: 24848285 - فاكس: 24837138
رأس المال: 1,000,000 د.ك - س.ت: 20117

** E.L. ADOBE ** EXTREME LINE COATING

DESCRIPTION: -

GTC Adobe decorative coating will remind you of the huts and haciendas of rural Mexico and Latin America.

GTC Adobe is a water based heavily structured decorative paste which offers aesthetic beauty and excellent exterior properties. It may be applied at any thickness without cracking or shrinking. Over-coating with Hi-Shade colour coat will give the final required appearance.

SPECIAL FEATURES: -

- ☐ Weather resistant.
- ☐ Water resistant.
- ☐ Flexible.
- ☐ Excellent adhesion.
- ☐ Long working time (Controlled drying).
- ☐ Easy application at any thickness.

AREA OF USE:

As a decorative and protective Exterior / Interior structured coat over new and old building surfaces i.e.,

- ☐ Interior ceilings of concrete and plastered walls.
- ☐ Concrete, GRC blocks
- ☐ Block works, brick works, stone ... etc
- ☐ Gypsum boards
- ☐ Wooden Surfaces

PRODUCT DATA: -

FINISH	: Matt/Lightly textured.
COLOUR	: White
VOLUME SOLID	: 62 %
PRODUCT WEIGHT	: 1.7
FILM THICKNESS	: As required.
THEO. COVERAGE	: Practical coverage depends on pattern and No. of coats.

NOTE: -

Coverage with decorative pastes has to be established by trials due to the wide variation in the patterns possible.

DRYING TIME:

SUBSTRATE TEMPERATURE	TOUCH DRY	HARD DRY	OVERCOATING INTERVALS	
			MINIMUM	MAXIMUM
10 °C (50 °F)	1½ hr.	7 hrs.	24 hrs.	IND.
25 °C (77 °F)	1 hour	6 hrs.	16 hrs.	IND.
40 °C (104 °F)	30 min.	5 hrs.	12 hrs.	IND.

GTC Paints Company Ltd.

P.O. Box: 24445 Safat - 13105 - Kuwait
Sabhan Tel.: 24710120 - Fax : 24761261
Shuwaikh Tel.: 24848285 - Fax : 24837138
Capital : K.D. 1,000,000 - C.R.: 20117



شركة أصباغ جي تي سي المحدودة

ص.ب: 24445 الصفاة - 13105 - الكويت
صباحان - تلفون: 24710120 - فاكس: 24761261
الشويخ - تلفون: 24848285 - فاكس: 24837138
رأس المال: 1,000,000 د.ك - س.ت: 20117

SURFACE PREPARATION:

NEW SURFACES :-

1. Degrease areas where grease, oil, soil and other surface contamination exist in accordance with **SSPC-SP1 Solvent Cleaning** . (Use **GTC002 Thinner**).
2. Wire Brush/Mechanical Power Tool Clean areas where laitance, surface porosity and loosely adhering foreign material exist in accordance with **SSPC-SP2** and/or **SSPC-SP3 Standards**
3. Surfaces to be coated must be dry, clean and contamination free prior to paint application process.

OLD/PREVIOUSLY PAINTED SURFACES :-:

1. Degrease areas where grease, oil and other surface contamination exist in accordance with **SSPC-SP1 Solvent Cleaning** . (Use **GTC002 Thinner**).
2. Remove all blistered, cracked and brittle paint coats off the surface.
3. Detached coats with inadequate adhesion must be properly scraped-off to a firm edge.
4. Glossy paint coatings must be sanded/roughened to ensure proper intercoat adhesion characteristics with successive paint coatings.
5. Surfaces to be coated must be dry, clean and contamination free prior to paint application process.

APPLICATION :-

Application to be done by stainless steel trowel followed by plastic trowel for structuring.

OVER-COATING :-

After complete drying of the applied Adobe coating apply 2 coats of **N. Drip Medium Gloss** of the required shade. After complete drying apply **Hi Shade** colour coat to produce the characteristic final appearance.

APPLICATION CONDITIONS :-

At a temperature ranging 5°C (41°F) to 40°C (104 °F) . Relative humidity is below 75%.

STORAGE & HANDLING :-

Product must be stored as per local regulations and should be kept in dry well ventilated location far from heat and direct sunlight. Can should be tightly closed after use. Mix well before use. Storage temperature range between 5°C (41°F) to 40°C (104 °F).

GTC Paints Company Ltd.

P.O. Box: 24445 Safat - 13105 - Kuwait
Sabhan Tel.: 24710120 - Fax : 24761261
Shuwaikh Tel.: 24848285 - Fax : 24837138
Capital : K.D. 1,000,000 - C.R.: 20117



شركة أصباغ جي تي سي المحدودة

ص.ب: 24445 الصفاة - 13105 - الكويت
صباحان - تلفون : 24710120 - فاكس : 24761261
الشويخ - تلفون : 24848285 - فاكس : 24837138
رأس المال : 1,000,000 د.ك - س.ت : 20117

SAFETY PRECAUTIONS :

The following notes should be considered when using/applying painting material:-

- (a) Take precautions to prevent material entering the eyes (goggles should be worn, irrigate the eyes with water when become contaminated and obtain medical care at once).
- (b) Take precautions to avoid skin contact (gloves should be worn, barrier cream should be used).
- (c) Ensure that repeated contact of paint with skin is avoided.
- (d) Provide adequate ventilation. (Face masks must be worn).
- (e) Keep away from sparks and open flames (for solvent-based materials).

DISCLAIMER:

- ☐ The information given in this data sheet is for guidance only and is done to the best of our knowledge at the date of printing/issuing.
- ☐ GTC reserves the right to change the content of this data without any prior notice.
- ☐ Since we have no control over either the nature or condition of the substrate or different factors which effect the use and application of our products; therefore, no liability can be accepted on basis of this data sheet, unless we specifically agree in writing as to the suitability of the recommended product for the intended purpose; and furthermore, application of this product should be carried out under our control and direct supervision.
- ☐ Product data are subject to change without notice and become void five years from the date of issue.

PACKING : 30 Kg Drum
ISSUANCE DATE : August 2017.
ORIGIN : Manufacture in Kuwait By GTC Paints Company Ltd.
ADDRESS : GTC PAINTS COMPANY
P. O. Box 24445 Safat, 13105 Safat, Kuwait
Tel. 24710120/24710170 Fax No. 24761261
Email : sales @ gtc.com