

GTC Paints Company Ltd.

P.O. Box: 24445 Safat - 13105 - Kuwait
Sabhan Tel.: 24710120 - Fax : 24761261
Shuwaikh Tel.: 24848285 - Fax : 24837138
Capital : K.D. 1,000,000 - C.R.: 20117



شركة أصباغ جي تي سي المحدودة

ص.ب: 24445 الصفاة - 13105 - الكويت
صباحان - تلفون : 24710120 - فاكس : 24761261
الشويخ - تلفون : 24848285 - فاكس : 24837138
رأس المال : 1,000,000 د.ك - س.ت : 20117

**** GETAPRIME (AWP012) **** **** WOOD PRIMER ****

PRODUCT DESCRIPTION:

A single-pack, solvent based Industrial and Priming Coat based on *Modified Alkyd Resin*; pigmented with *Leafing and Non-Leafing Aluminium Paste* intended for application over wooden surfaces.

SPECIAL FEATURES:

- ☐ Excellent sealing properties.
- ☐ Flexible and relatively quick drying.
- ☐ Resistant to moisture and humid conditions.
- ☐ Easy to apply and has excellent covering power.
- ☐ Applicable over resinous and non-resinous wooden surfaces.
- ☐ Preserves wood from bacteria and fungul attack.

AREA OF USES:

A priming coat specially developed for protection of Interior/Exterior wooden surfaces intended for overcoating with alkyd paints i.e.,

- ☐ Wood Paneling
- ☐ Wooden Frames
- ☐ Doors

PRODUCT DATA:

FINISH	:	METALIC
COLOUR	:	Aluminium
VOLUME SOLID	:	55 %
PRODUCT WEIGHT	:	1.0 kg/ltr.
REC. FILM THICKNESS	:	Wet : 45 microns per coat (approx. 1.8 mils) Dry : 25 microns per coat (approx. 1 mil)
THEO. COVERAGE	:	22 m ² /ltr.

Practical coverage primarily depends upon nature of surface profile, method of application and site conditions.

FLASH POINT	:	Above 35 °C (95 °F)
-------------	---	---------------------

GTC Paints Company Ltd.

P.O. Box: 24445 Safat - 13105 - Kuwait
Sabhan Tel.: 24710120 - Fax : 24761261
Shuwaikh Tel.: 24848285 - Fax : 24837138
Capital : K.D. 1,000,000 - C.R.: 20117



شركة أصباغ جي تي سي المحدودة

ص.ب: 24445 الصفاة - 13105 - الكويت
صباحان - تلفون : 24710120 - فاكس : 24761261
الشويخ - تلفون : 24848285 - فاكس : 24837138
رأس المال : 1,000,000 د.ك - س.ت : 20117

DRYING TIME:

SUBSTRATE TEMPERATURE	TOUCH DRY	HARD DRY	OVERCOATING INTERVALS	
			MINIMUM	MAXIMUM
10 °C (50 °F)	4 hrs.	30 hrs.	24 hrs.	14 days
25 °C (77 °F)	3 hrs.	24 hrs.	20 hrs.	14 days
40 °C (104 °F)	2 hrs.	18 hrs.	16 hrs.	14 days

STANDARDS & APPROVALS:

Supportive information is available upon request to establish an assessment to be acquired as with regards to product's compliance with/to a particular authority's queries / specifications. *Please consult with GTC Technical Service Dept.*

SURFACE PREPARATION:

1. Surfaces to be coated must be dry, clean, and free from oil, grease, ... etc. in accordance with **SSPC-SP1 Solvent Cleaning**.
2. Wood must not contain more than 17% moisture.
3. Surface must be sanded and/or ground to eliminate surface imperfections.

APPLICATION DETAILS:

☐ PURPOSE OF USAGE:

Intended for **a single or two coat applications** over well prepared surfaces and to be overcoated with **Conventional Paint Coatings**.

☐ MIXING AND THINNING:

Material must be properly mixed and is recommended for thinning with **GTC002 Thinner** as per below table:-

APPLICATION METHOD	BRUSH/ ROLLER	CONV. SPRAY	AIRLESS SPRAY
Thinning by volume (% Max.)	10%	15%	5%

☐ NOTES:

- ☐ Best results can be achieved by **brushing on first coat** as this method provides maximum penetration and adhesion into the substrate.
- ☐ When applied as a partial coat of a recommended scheme against **"FIRE RETARDANT SYSTEM"** it is required to apply this material at 50 microns D.F.T. (approx. 2 mils).

☐ CLEANING:

For cleaning tools and equipments use **GTC002 Thinner**.

GTC Paints Company Ltd.

P.O. Box: 24445 Safat - 13105 - Kuwait
Sabhan Tel.: 24710120 - Fax : 24761261
Shuwaikh Tel.: 24848285 - Fax : 24837138
Capital : K.D. 1,000,000 - C.R.: 20117



شركة أصباغ جي تي سي المحدودة

ص.ب: 24445 الصفاة - 13105 - الكويت
صباحان - تلفون : 24710120 - فاكس : 24761261
الشويخ - تلفون : 24848285 - فاكس : 24837138
رأس المال : 1,000,000 د.ك - س.ت : 20117

APPLICATION CONDITIONS :-

At a temperature ranging 5°C (41°F) to 40°C (104 °F) . Relative humidity is below 75%.

STORAGE & HANDLING :-

Product must be stored as per local regulations and should be kept in dry well ventilated location far from heat and direct sunlight. Can should be tightly closed after use. Mix well before use. Storage temperature range between 5°C (41°F) to 40°C (104 °F).

SAFETY PRECAUTIONS:

The following notes should be considered when using/applying painting material:-

- Take precautions to prevent material entering the eyes (goggles should be worn, irrigate the eyes with water when become contaminated and obtain medical care at once).
- Take precautions to avoid skin contact (gloves should be worn, barrier cream should be used).
- Ensure that repeated contact of paint with skin is avoided.
- Provide adequate ventilation. (Face masks must be worn).
- Keep away from sparks and open flames (for solvent-based materials).

DISCLAIMER:

- ◆ The information given in this data sheet is for guidance only and is done to the best of our knowledge at the date of printing/issuing.
- ◆ GTC reserves the right to change the content of this data without any prior notice.
- ◆ Since we have no control over either the nature or condition of the substrate or different factors which effect the use and application of our products; therefore, no liability can be accepted on basis of this data sheet, unless we specifically agree in writing as to the suitability of the recommended product for the intended purpose; and furthermore, application of this product should be carried out under our control and direct supervision.
- ◆ Product data are subject to change without notice and become void five years from the date of issue.

PACKING : ☐ Gallon
 : ☐ 18 Ltr. Drum
ISSUANCE DATE : August 2017
ORIGIN : Manufacture in Kuwait by GTC Paints Company Ltd.
ADDRESS : **GTC PAINT COMPANY LTD.**
 P.O.Box 24445 Safat, 13105 Safat, Kuwait
 Tel : 24710120/24710170 - Fax : 24761261 .
 Email : sales @ gtcpaints.com